

Papeles prensa de alta calidad 100% fibra reciclada, con excelente maquinabilidad y alta imprimibilidad.

L* a* b* Valores objetivo	L*	a*	b*
ISO 13655 (D50/2°)	85	1	-3

Valores objetivo

TEST	NORMA	UNIDAD	AiAPrint CS				
Gramaje	ISO 536	g/m ²	40	42	45	48.8	52
Blancura	ISO 2470-1 (C/2°)	%	58.5	58.5	58.5	58.5	58.5
Opacidad	ISO 2471	%	92	92	92	93	94
Mano	ISO 534	cm ³ /g	1.45	1.45	1.45	1.45	1.45
Lisura	PPS, ISO 8971-2	µm	4.1	4.1	4.1	4.1	4.1

