

CEPI code 50

TL4 light produced in wide variety of grammages with regular and excellent runnability.

Typical Value

TEST	STANDARD	DIMENSION	AiANature TL	
Basis Weight	ISO 536	g/m ²	85	90
Nominal Humidity	ISO 287	%	8	8
Bursting Strength	EN ISO 2758	kPa	135	150
SCT, DT	ISO 9895	kN/m	1.35	1.40

Guaranteed Value

TEST	STANDARD	DIMENSION	AiANature TL	
Basis Weight	ISO 536	g/m ²	85	90
Variation			+ - 2	+ - 2
Nominal Humidity	ISO 287	%	8	8
Variation			+ - 1	+ - 1
Bursting Strength	EN ISO 2758	kPa	130	145
SCT, DT	ISO 9895	kN/m	1.30	1.30

